


# Old London

**SANDSTONE** | WORN & PATINATED

Good quality reclaimed sandstone is hard to find and expensive. It's not just the intrinsic quality of this stone that makes it such a good match, but the way that stones from different beds are mixed to mimic the varied tones and textures of old slabs, and the colour-enhancing coating that is applied.

Suitability: Domestic/heavy commercial interior floors, sealing required



CREDIT: Project by SHH Architects

## Formats

**Format**

60 x Random x 2.2cm

**Availability**

Usually in stock

## Technical Data

Test	Standard	Result
Apparent Density	BS EN 1936 : 2006	2659Kg/m <sup>3</sup>
Open Porosity	BS EN 1936 : 2006	0.2%
Water Absorption at Atmospheric Pressure	BS EN 13755 : 2008	2.8%
Flexural Strength (3 Point)	BS EN 12372 : 2006	30.1MPa
Frost Resistance (56 Cycles)	BS EN 12371 : 2010	3MPa
Abrasion Resistance	BS EN 14157 : 2004	20.5mm
Slip Resistance (Dry)	BS EN 14231 : 2003	PTV 34.3
Slip Resistance (Wet)	BS EN 14231 : 2003	PTV 19.5

- ✓ Suitable for use with underfloor heating
- ✓ Suitable for use in freezing temperatures

**For any further information or advice, please contact our team.**

### Installation, Care & Maintenance Advice

Please refer to the installation guides on our website.