


Blandford

LIMESTONE | TUMBLED

This soft, pale beige limestone with its minute fossils and uniform tone takes beautifully to both the honed and tumbled finishes- the perfect, neutral backdrop to all design styles.

Suitability: Domestic/light commercial interior floors, sealing required



Formats

Format

60 x Random x 2cm

Availability

Usually in stock

Technical Data

Petrographic Details

Biopelsparitic Limestone

Test	Standard	Result
Apparent Density	BS EN 1936 : 2006	2390kg/m ³
Open Porosity	BS EN 1936 : 2006	9.8%
Water Absorption at Atmospheric Pressure	BS EN 13755 : 2008	4.3%
Flexural Strength (3 Point)	BS EN 12372 : 2006	10.4MPa
Frost Resistance (56 Cycles)	BS EN 12371 : 2010	11.6MPa
Abrasion Resistance	BS EN 14157 : 2004	22mm
Slip Resistance (Dry)	BS EN 14231 : 2003	PTV 64.5
Slip Resistance (Wet)	BS EN 14231 : 2003	PTV 35.7

- ✓ Suitable for use with underfloor heating
- ✓ Suitable for use in wet areas

For any further information or advice, please contact our team.

Installation, Care & Maintenance Advice

Please refer to the installation guides on our website.